



**EN 13034 PROTECTIVE CLOTHING WITH LIMITED PROTECTIVE
PERFORMANCE AGAINST LIQUID CHEMICALS
(TYPE 6 AND TYPE PB [6] EQUIPMENT)
TEST METHODS AND REQUIREMENTS**

Check of the design	EN 13034, part 5.1
Check of the ergonomic features	EN ISO 13688
Check of size designation	EN ISO 13688
pH-value	ISO 3071
Pretreatment: Washing and drying	EN ISO 15797 (industrial) or EN ISO 6330 (domestic)
Dimensional change due to cleaning	ISO 5077 after 5 cycles
Abrasion resistance	EN 530 Method 2 after pretreatments
Trapezoidal tear resistance	EN ISO 9073-4 in warp and weft direction after pretreatments
Tensile strength	EN ISO 13934-1 in warp and weft direction after pretreatments
Puncture resistance	EN 863 after pretreatments
Liquid repellency	EN ISO 6530 after pretreatments
Resistance to penetration by liquids	EN ISO 6530 after pretreatments
Seam strength	EN ISO 13935-2 after pretreatments
Resistance to penetration by liquids in the form of a light spray (mist test)	EN 13034, part 5.2 after pretreatments